

ACCURATE ALGINATE IMPRESSIONS



» INDICATIONS:

When a chef is first learning to bake something new, he will usually follow the recipe very closely. However, once he has made the dish a few times, he will often begin to tinker with the ingredients. Maybe he will add an extra pinch of salt or a little less flour. Modifying the recipe like this may work well when cooking, but it can become a nightmare when doing dentistry.

Taking an alginate impression is one of the most common procedures done in the dental office. In fact, if you follow directions, it should be as easy as baking a cake. But like baking, if the dentist changes the dental impression recipe without thinking about how it is going to affect the result, it can lead to failure. For example, simply adding a little extra water to alginate can adversely change the water/powder ratio, thinning the mix and increasing the setting time.

Unfortunately, because taking an alginate impression appears to be so easy, it has become one of the most abused techniques in dentistry. Not taking the time to do this procedure correctly is one of the most expensive mistakes you can make in your dental practice.

» DESCRIPTION:

Dental alginate is the most widely used impression material. Its wide use is a result of its low cost, ease of manipulation, need for minimal

equipment, and acceptable accuracy for many dental procedures. Some of the more common procedures which can be accomplished using alginate are:

- Impressions for partial dentures.
- Primary impressions in edentulous mouths.
- Impressions for diagnostic casts.
- Impressions for removable and fixed orthodontic appliances.
- Master casts impressions for dental sleep apnea appliances.
- Impressions for splints and night guards.
- Impressions for opposing casts for crown & bridge work.^{1,2}

Dental alginate is an impression powder that, when mixed with water, will undergo a series of chemical reactions that will take it from a viscous sol to an elastic gel.^{1,2,3} A typical formula for an alginate impression powder is:

- *Potassium or Sodium alginate* - the chief ingredient which comes from sea kelp and forms a sol in water.
- *Calcium sulfate* - reacts with potassium or sodium alginate to produce a gel.
- *Trisodium phosphate* - retards the reaction to provide more working time.
- *Diatomaceous earth* - a filler used to control the consistency of the mix and the strength and flexibility of the impression.
- *Potassium zinc fluoride* - used to counteract an inhibiting effect that alginate has on the setting of the gypsum.
- *Organic glycol* - used to coat the powder particles to minimize the dust during dispensing.
- *Quaternary ammonium compounds* - Sometimes added as a self disinfection agent.¹

These ingredients allow alginate to:

1. Easily be mixed in water to form a viscous gel.
2. Have enough body to be contained in an impression tray.
3. Have enough working time to be carried to the mouth.
4. Change into an elastic gel once it is placed in the mouth
5. Be removed from the mouth without distortion and to have enough strength and stiffness to insure a firm surface.²

Alginate is available in both individual packages and bulk containers. Although bulk alginate is used more often because of its lower initial cost, packages containing only enough alginate for an individual impression are preferred. These packages minimize moisture contact with the powder and extend the storage life of the alginate.¹

Regardless of how it is dispensed, alginate should always be stored in a dry place where the temperature is maintained between 50° and 80° Fahrenheit. It is best to discard material has been stored over one year.²

» TREATMENT PROCEDURES

The following is a list of the precise, step by-step procedures that must be followed exactly in order to obtain an impression and a cast that will meet the high standards of treatment desired for your patients.

1. Pick an appropriate impression tray.
 - a. The selection of the proper size and shape of the tray is essential. A properly sized tray must include all the areas wanted in the impression and still allow for adequate clearance between the tray and the tissues. If this is not done the impression will distort or tear upon removal from the mouth.

b. Many different tray types can be used ranging from disposable plastic to metal perforated trays. We recommend the use of a metal rim lock tray for two reasons. First, because alginate is a compressive material a solid tray will force the material around the teeth better than a perforated tray. Second, the rim-lock design will hold the impression material in place without the need of an adhesive.



Solid rim lock trays are best for alginate impressions

2. Prepare to take an impression by placing your alginate, rubber mixing bowl, spatula, and alginate measuring instruments on the counter.
3. Accurately measure out the amount of powder and water you will need to take an impression.
 - a. If you choose to use alginate from bulk containers always make sure to shake the can to insure an accurate measurement of the material as it tends to settle when its left on the shelf.^{1,2,3}
 - b. One scoop of powder should be used for every mark on the water cup. When dispensing the powder, over fill the cup, tap it lightly, then remove the excess from the top.^{1,2}
 - c. Distilled water is recommended for use with all alginate mixes because it will eliminate contamination of the mix with calcium, fluoride and other materials often found in tap water.
 - d. The temperature of the water should be at 21° C (70F).^{1,2,3} (See Contraindications and Concerns)
4. Just before taking the impression, have the patient rinse to cut the mucin and lower the surface tension. Then, lightly dry the teeth with compressed air just prior to insertion of the impression material and the tray. Do not over dry the teeth as the material may tend to stick to the teeth when the impression is removed.

5. Slowly add the powder to the water making sure to incorporate all the powder into the mix. The alginate should then be mixed vigorously by pressing the alginate between the mixing bowl and the spatula until a smooth creamy consistency - free of graininess - is reached. Mixing time should be 1 minute for regular set alginate and 45 seconds for fast set alginate. If the material is under mixed, the chemical reaction will not proceed uniformly throughout the mass. This can decrease the strength of the gel by 50%. On the other hand, over mixing also decreases the gel's strength, as too much spatulation will break up the gel as it forms.²
6. After the impression material is mixed, place the alginate in the tray in small amounts, and make certain that you force the material into the rim-locks of the tray. Then, dip your finger in cold water and smooth the surface of the alginate.¹
7. Take some of the excess impression material and forcefully press it into the vestibule and on the occlusal, buccal, and lingual surfaces of the teeth. If a high palatal vault exists, place some there as well.
8. Insert the filled tray immediately, gently jiggling it into place until it is completely seated. Maintain only enough pressure to hold the tray in place making sure to avoid moving the tray until after gelation is complete. If the tray is moved during gelation, strains will be incorporated in the alginate. Upon removal of the impression from the mouth, these strains will be released, cause distortion of the impression, and make the cast inaccurate.
9. Always keep a small test sample of the alginate in your mixing bowl. When this sample loses its tackiness gelation has begun. Then, wait another full two minutes before attempting to remove the impression. Waiting several minutes after the initial gelation increases both the tear and compressive strength of the material.
10. Remove the impression with a firm, quick snap. Do not rock or twist the impression before removing it. An alginate impression is easily deformed if it is removed slowly, but it is not permanently distorted if it is removed quickly.

11. As soon as the impression is removed from the mouth, inspect it carefully for defects.
12. With a water air syringe, rinse the impression free of any blood or saliva. Shake out as much of the excess water as you can, then lightly blow the rest away with the air syringe being careful not to dry out the impression.
13. Disinfect the impression. All impressions should be rinsed and disinfected before they are poured up and sent to the lab. Sodium hypochlorite, iodophor, glutaraldehyde and phenylphenol solutions are all being used, and some manufacturers have even added disinfectants to the alginate powder.^{1,2,3,4,5,6,7} (See Contraindications and Concerns)
14. All impressions should be poured immediately with vacuum-mixed stone and with the use of a vibrator.
15. Accurately measure out an appropriate amount of stone and water. Stone requires a water/powder ratio of .30 or 30g of water for every 100g of stone.¹
16. Slowly add the stone to the water to insure that all the powder is completely incorporated. Then vacuum mix the mixture.¹ The consistency of the stone should be that of a pseudoplastic viscous liquid which has a glossy surface to it.¹
17. Holding the impression on a vibrator, start adding stone in the molar region of one side. Slowly allow the stone to work its way around the impression. Continue adding stone to the same side until the impression is completely poured.
18. Once the impression has been poured, hang it on an impression tree, wrap it in a moist paper towel and let it set up. Models that harden in 100% humidity have a superior stone surface.
19. Give a minimum of thirty minutes but not longer than one hour for the stone to set up. Then separate the alginate impression from the stone model. All alginate materials contain alginic acid which, if left in contact with stone too long, will "eat into it" and give the stone a moth-eaten appearance. To avoid this problem, remove the cast immediately after it has an adequate set.



Using an impression tray tree will allow your cast to setup distortion free.

20. Evaluate the stone model carefully. Check to make sure that you have recorded all the areas necessary to achieve a successful result and that the model is distortion free.

» SUPPLY LIST

- Vinyl mixing bowl*
- Wide blade spatula*
- Alginate*
- Distilled water
- Impression trays* (We recommend a Rim Lock design)
- Adhesive* (This is necessary with a Plastic tray)
- Laboratory Vibrator
- Yellow stone (Do not use plaster)
- Vacuum mixer
- Impression Tray Tree*
- Disinfectant

*Available from Success Essentials, call 1-800-423-3270

» CONTRAINDICATIONS AND CONCERNS

Alginate does not reproduce fine detail as reliably as do the other elastomeric impression materials. This may be due to the somewhat more porous surface of the impression material or to a reaction between the stone and the irreversible hydrocolloid. Therefore alginate is not accurate enough for crown and bridge impressions.

All impressions should be rinsed and disinfected before they are poured up and sent to the lab. The goal in choosing a method to disinfect alginate impressions is to select a material that will work without affecting the accuracy of the impression. Sodium hypochlorite, iodophor, glutaraldehyde and phenylphenol solutions are all being used. It is always best to follow the manufacturer's instructions since some companies have already added

disinfectants to their alginate powder. There are occasions when you will need to vary the setting time of the alginate. For example, if your patient gags you may want the alginate to set faster. This can be controlled by varying the temperature of the water. Warmer water allows the mix to set faster than cold water. Never control the setting time by varying the consistency of the mix. Changing this ratio will also effect the impressions permanent deformation, flexibility and strength.^{1,2,3}

Alginate impressions lose their accuracy rather quickly. If the impression is stored in air, water evaporates and the impression shrinks. If it is stored in water it will absorb the water and expand. Therefore it is always best to pour up an alginate impression immediately. But, when you cannot, keep it in a humidor. Storing it in 100% relative humidity will give you about an hour before serious dimensional changes occur.^{1,2,3}

Always allow your poured impression to set up in the tray with the teeth down. As stone sets in an alginate impression excess water in the stone mix rises to the highest point. If the tray is turned upside down onto a base of stone, that water will go to the cusp tips. This could result in faulty shaped cusp tips that are very soft.⁴

Never let an alginate impression sit on a bench top. If You place the impression with the alginate side down, the weight of the tray can deform the impression. If you place the impression with the tray side against the bench, any untrimmed excess alginate can deform the impression, Therefore, it is always best to use a tray tree to hold your impressions.

» TROUBLE SHOOTING

If my impressions are not coming out accurately, how can I find out where I'm making a mistake? The following is a list of the most common problems and their causes.

1. The consistency of the alginate is grainy.
 - a. Improper mixing- add the powder to the water to make sure that all of it is incorporated into the mix. Then mix vigorously for one minute to get a creamy consistency.



Never place an impression on the bench - always use a tray tree!

2. Incorrect water/powder ratio- too much powder in the mix usually occurs because the alginate was not fluffed up in the can before measuring it out.
 - a. Inadequate thickness of the material. If the material is too thin it will usually tear. This is directly related to having too much water in the mix.
2. Premature removal from the mouth. The impression must be left in the mouth for full 2 minutes after your test sample has begun to set in the mixing bowl. Alginate doubles its tear strength in this time period.
 - a. Inadequate thickness of the material. If the material is too thin it will usually tear. This is directly related to having too much water in the mix.
 - b. Premature removal from the mouth. The impression must be left in the mouth for full 2 minutes after your test sample has begun to set in the mixing bowl. Alginate doubles its tear strength in this time period.
3. Incorrect removal technique. Remember, alginates are less likely to tear during removal from the mouth when they are removed rapidly. Therefore remove the impression with a snap.
 - a. Premature removal from the mouth. If the material is still in a plastic state, detail will be lost.
 - b. Moisture or debris in the mouth . Remember to always have the patient rinse thoroughly before taking their impression.
4. The surface of the stone model is rough or chalky.
 - a. Inadequate cleaning and drying of impression- Always rinse the alginate impression thoroughly with water to clean out any blood or saliva. Then shake out as much of the excess water as you can and rightly blow the rest



Inverting the tray will cause the stone to flow away and excess water to move towards the teeth

of it away with an air syringe. Do not over dry the impression.

b. Incorrect handling of the gypsum-excess water in the mixture can cause the stone to be soft and chalky. This is especially true if you turn the impression over onto a base of stone as all the excess water will move towards the teeth.

c. Failure to separate the cast after one hour- the alginic acid in the alginate will cat away at the stone if it is left in contact too long.

5. The model came out distorted and inaccurate.

a. Delayed pouring of an impression - whenever possible pour tip your impression immediately. If you keep the impression in a humidifier, you still have only 1 hour before your impression will be too distorted to use.

b. Inadequate retention of impression material in the tray- if the impression material pulls away from the tray, redo the impression. Even if it fits back into the tray perfectly, do not use it. It is distorted!

c. Incorrect technique used to remove the impression from the mouth - alginate must be removed quickly with a snap. Slow removal will permanently distort the impression.

d. Premature removal from the mouth - remember to wait a full two minutes after your sample alginate has set up in the mixing bowl.

e. Movement of tray during gelation - If the tray is moved during this period, strains will be incorporated in the alginate. On removal of the impression from the mouth, these strains will be released, causing distortion of the impression.

»» LAB REQUIREMENTS

At Space Maintainers, we evaluate hundreds of models every day. Our

people are trained to recognize a distorted model. But even the best trained eye can miss a subtle distortion. Therefore, the key to having the lab produce a quality product is to give us a quality model which is distortion free. To do this you must start at the beginning by taking an excellent impression. There is an old saying that I learned in dental school: "The impression you take is the impressions you make."

Nothing is more frustrating than sitting down to deliver an appliance only to find it doesn't fit. To make matters worse, we usually try to make the appliance fit so we won't be faced with the annoyance and the embarrassment of having to take another impression. Most of the time this situation could have been avoided by following the guidelines recommended in this Practice Building Bulletin.

In many offices, the chairside assistant is responsible for taking alginate impressions and pouring them up in stone. Therefore to get consistently successful results, we recommend the following:

1. Make copies of this bulletin and share it with your staff.
2. Make sure your staff has all the tools they will need to be successful (see Supply List).
3. Take the time to check your impressions before they are poured up in stone.
4. If you are unsure that your impression is good, take another one now!
5. Always carefully check your models for accuracy before you send them to the lab.

In a busy practice, it may not be easy to find the time to check an alginate impression for accuracy or stop what you are doing to check your models before they go to the lab ... but believe me, doing so will save you time, money, and a lot of heartache.

»» INCOME POTENTIAL

Every time you have to repeat a procedure it's like flushing money down the cuspidor. With the high cost of running a dental office, you could lose \$500 or more for every hour of lost appointment time.

Equally important but more difficult to measure are the costs of unhappy patients, lab work that doesn't fit, poor relations with your lab, and an over-stressed and unhappy staff.

In today's economic environment, any steps you can take to make your office run more efficiently are of the utmost importance. If you follow the instructions in this practice building bulletin, taking an accurate alginate impression can really be as easy as baking a cake.

By **Rob Veis D.D.S.**
Director of Practice Development

»» REFERENCES

1. Craig, Robert PhD.: Dental Materials, Properties and Manipulation, Fifth Edition, C.V. Mosby Co., St. Louis, 1992, pp61-172.
2. Phillips and Moore: Elements of Dental Materials for Dental Hygienists and Dental Assistants, Fifth Edition, W.B. Saunders, Phil. 1994, pp86-73.
3. O'Brien, William J.: Dental Materials Properties and Selection, Quintessence, Chicago, 1989, pp77-186.
4. Pfitzinger, Walt: How to do Simple Orthodontics in the General Practice, Space Maintainers Laboratory Manual, Chatsworth, 1992.
5. Waiters, Ray: A Practical Irreversible Hydrocolloid Impression Tray Holder, The Journal of Prosthetic Dentistry, Vol 64, Number 5 1990, pp625-626.
6. Rueggeberg, Beall, Kelly and Schuster: Sodium hypochlorite disinfection of irreversible hydrocolloid impression material, The Journal of Prosthetic Dentistry, Vol 67, Number 5, May 1992, pp628-631.
7. Jones, Newcombe and Bottomley: The dimensional stability of sclt-disinfecting alginate impressions compared to various immersion regimes, The Angle Orthodontist, Vol 60, Number 2, pp23-1 28.

The Practice Building Bulletin is a special service of Space Maintainers Laboratory produced solely for the private use of our clients. It is designed to help expand and enhance your ability to provide comprehensive patient care. Information included is the opinion of the author and may not be reproduced in any form without written consent.

Appliance Therapy Group Headquarters:

Space Maintainers Laboratory
9139 Lurline Ave. Chatsworth CA 91311
Copyright © 2009

www.ApplianceTherapy.com

Regional Labs:

Southwest	800-423-3270
Northwest:	800-423-6509
Northeast	866-310-5800
Southeast	800-289-0118
Midwest:	800-325-8921
CANADA	800-661-1169
AUSTRALIA	03-9521-0299
MALAYSIA	03-621-8599
TAIWAN	886-7-235-5612